



NORTH SEA RESINS

NSR150 USAGE INSTRUCTIONS

Directions for use:


Syringe cap twists on and off for multiple uses of resin. The product is light sensitive and exposure to daylight will initiate curing process. When cured in an open-air (oxygen) environment, a slightly tacky surface will result. **Use of North Sea Resins® (NSR) applicator tabs are recommended for applications that prefer a tack-free surface.** A light sanding with 150 grit sandpaper is recommended prior to application of the resin. For optimal adhesion, the surface should be clean of dust and dirt. An important consideration is the resin will cure-on-command only if the appropriate light reaches the resin.



1. Pipe with pin hole. Relieve pressure. Surface can be wet or dry.



2. Clean/roughen area with 150 grit sandpaper.



3. Cut Applicator Tab to desired size. Apply resin to NSR Tab.



4. Using NSR Tab, apply gentle pressure.



5. Shine NSR High Intensity Light directly on the applicator tab/resin for 30 seconds or until fully cured.



6. Remove NSR Tab. Completed repair. Note resin covers an area larger than the actual hole.

For larger holes (1/4" or greater) use of fiberglass mesh is recommended. Lay fiberglass mesh on NSR Applicator Tab. Apply resin to mesh material so it is fully moist. Follow steps 4 & 5 from above. Apply a second coat of resin on top of mesh to insure a strong repair. **Sand off any fiberglass strands. Do not pull.**



1. Quarter inch hole.



2. Apply resin to tab/mesh until fully moist.



3. Sand fibers.



4. Finished repair.

Storage and Shelf Life:

This product is light sensitive. Store in original container. Store product at 60-80°F or refrigerate for maximum shelf life.

Shelf life is 24 months when stored at 60-80°F.

Precautionary Information:

Refer to Material Safety Data Sheet for health and safety information before using this product.

Important Notes:

Data contained herein are furnished for information only and are believed to be reliable. Due to the variety of factors that can affect the use and performance of a North Sea Resins® (NSR) product, some of which are uniquely within the user's knowledge and control, user is responsible for determining whether the NSR product is fit for a particular purpose and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. NSR makes no warranties, expressed or implied, including but not limited to, any implied warranty of merchantability or fitness for a particular purpose.

If NSR product is proved to be defective, the exclusive remedy, at NSR's option, shall be to refund the purchase price of or to repair or replace the defective NSR product. NSR disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of NSR products. NSR specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.